


Product Technical Information

ITA/ATEXP/234
Rev.6 – 03/04/14
Page 1/2

ADEPAR JS

DESCRIPTION AND SCOPE OF APPLICATION

Underlayer of self protected two layers system when partial bonding is required for new works and reproofing on allowed supports..



COMPOSITION

Main surface	Macroperforated film with sand on the holes
Longitudinal overlap surface	Siliconed Kraft paper
Blend	Fillerized SBS (Styrene-Butadiene-Styrene) elastomeric bitumen
Reinforcement	Non woven composite
Underface	Self-adhesive edges and strips, protected by siliconised peel-off film.

DIMENSIONAL CHARACTERISTICS

	Nominal value	Critical value
Thickness on the longitudinal selvedge (mm)	2.65	2.5
Thickness on the main surface (mm)	2.65	2.5
Longitudinal selvedge width (mm)	60	50
Roll length and width (m)	10 x 1	9.9 x 0.99

PERFORMANCES

KIND OF TEST	Reference Norm	Units	Nominal values	Critical values
Tensile strength at max	EN 12 311-1	N/50mm	650 x 350	550 x 315
Elongation at max	EN 12 311-1	%	35 x 35	23 x 30
Nail tearing resistance	EN 12 310-1	N	200 x 200	150 x 150
Cold temperature flexibility	EN 1109	°C	≤ - 20	- 15
Heat flow test	EN 1110	°C	≥ 100	100
Dimensional stability	EN 1107-1	%	≤ - 0.5	-
Shear joint resistance (side lap x head lap)	EN 12317-1	N/50mm	400 x 600	-
Impact resistance (hard substrate)	EN 12691	mm	600	-
Waterproofing	EN 1928	-	Pass	-

ISO 9001 REFERENCE DOCUMENT

Our company has been awarded the ISO 9001 certificate for all its establishments in France.

Our company reserves the right to modify its composition as a result of technological and experimental improvements.

To obtain the up-date technical data sheet, please contact Siplast

07559P Spc v12 9/7/13



Product Technical Information

ITA/ATEXP/234
Rev.6 – 03/04/14
Page 1/2

PACKAGING

Rolls quantity per truck pallet	24
Rolls quantity per container pallet	27
Rolls quantity per wooden box	25
Nominal weight / m ² (kg/m ²)	3.5
Nominal weight / roll (kg)	35

GENERALITIES ABOUT APPLICATION

Using	The generalities about the product using are set out in the ZSA STANDARD
Application	The generalities about the product application are set out in the ZTA STANDARD
Overlaps	Current building practices concerning overlaps are set out in the ZRA STANDARD
Slopes	Current building practices concerning slopes are set out in the ZPA STANDARD

COMPLEMENTARY INFORMATIONS

Product identification	
Values	Where 2 values for given characteristics are shown, the first is for longitudinal direction and the second is for the cross direction.
Tolerances	The average values derived from standard tests and are subject to the usual production variations. The indicated average values comply with the UEAtc standard and EN 13707. The nominal value tolerances comply with the UEAtc standards. Some slight variations can be noticed as the values are based on the average values obtained from several plants.
Modification(s)	Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the up-date technical data sheet, please contact our technical department.
Hazardous classification	It is not classified as dangerous according to the international regulation (ADR, RID, IATA, et RTMDR)
Divers	This product is only a product technical data sheet, regarding each waterproofing design, please, consult the concerned technical agreement and in case of doubt contact our technical department.
Storage	This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.