

Product Technical Information

ITA/ATEXP/201
Rev.8 - 20/05/14
Page 1/2

PARADIENE 30.1 GS

DESCRIPTION

Very high performance reinforced SBS elastomeric bitumen membrane with self protected coloured granules for waterproofing works.

This product is for use as :

- Toplayer of two-layers system self protected or under heavy protection.

COMPOSITION

Main surface	Coloured granules/slate
Longitudinal overlap surface	Sanded
Blend	Fillerized SBS (Styrene-Butadiene-Styrene) elastomeric bitumen
Reinforcement	Glassmat
Underface	Thermo-fusible film.

DIMENSIONAL CHARACTERISTICS

COLOURS	Slate grey 30 and Schist light 1		Others colours	
	Nominal value	Critical value	Nominal value	Critical value
Thickness on the longitudinal selvedge (mm)	2.6	2.5	2.6	2.5
Thickness on the main surface (for information only) (mm)	3,4	3.3	3.6	3.5
Longitudinal selvedge width (mm)	70	63	70	63
Weight / m ² (kg/m ²)	4.20	3.99	4.57	4.34
Weight / roll (kg)	41.7	39.6	45	42.8
Roll length and width (m)	1 x 10	0.99 x 9.90	1 x 10	0.99 x 9.90

PERFORMANCES

KIND OF TEST	Reference Norm	Units	Nominal values	Critical values
Tensile strength at max	EN 12 311-1	N/50mm	350 x 200	320 x 190
Elongation at max	EN 12 311-1	%	2.5 x 2	2.2 x 1.9
Cold temperature flexibility	EN 1109	°C	≤ - 20	≤ - 15
Heat flow test	EN 1110	°C	≥ 100	≥ 100

ISO 9001 REFERENCE DOCUMENT

Our company has been awarded the ISO 9001 certificate for all its establishments in France.

Our company reserves the right to modify this document as a result of technological and experimental improvements.

To obtain the up-date technical data sheet, please contact Siplast

07557N Spc v8 4/7/13



Product Technical Information

ITA/ATEXP/201
Rev.8 - 20/05/14
Page 2/2

PACKAGING

COLOURS	Slate grey 30 and Schist light 1	Others colours
Rolls quantity per truck pallet	24	23
Rolls quantity per container pallet	25	25
Rolls quantity per wooden box	24	23

APPLICATION

Using	The generalities about the product using are set out in the ZSA STANDARD
Application	The generalities about the product application are set out in the ZTA STANDARD
Overlaps	Current building practices concerning overlaps are set out in the ZRA STANDARD
Slopes	Current building practices concerning slopes are set out in the ZPA STANDARD

COMPLEMENTARY INFORMATIONS

Product identification	
Values	Where 2 values for given characteristics are shown, the first is for longitudinal direction and the second is for the cross direction.
Tolerances	The average values derived from standard tests and are subject to the usual production variations. The indicated average values comply with the UEAtc standard and EN 13707. The nominal value tolerances comply with the UEAtc standards. Some slight variations can be noticed as the values are based on the average values obtained from several plants.
Modification(s)	Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the up-date technical data sheet, please contact our technical department.
Hazardous classification	It is not classified as dangerous according to the international regulation (ADR, RID, IATA, et RTMDR)
Complementary information	This product is only a product technical data sheet, regarding each waterproofing design, please, consult the concerned technical agreement and in case of doubt contact our technical department.
Storage	This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.